

100 % extra long staple cotton yarn, royalspun

SwissCotton Royal - 100 % extra long staple cotton yarn: yarn on cones

Garnnummer			Zugfestigkeit (5000mm/min.) *		Dehnung *	Egalität **	Imperfektionen **			Haarigkeit **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Dünn -50%	Dick +50%	Nissen +200%	H
12	20	0.8	25.8	4.9	6.5	7.1	0	2	1	7.5
20	34	0.8	27.1	4.8	6.6	8.9	0	4	4	5.0
24	40	0.8	26.8	5.0	6.5	9.0	0	3	5	5.3
30	50	0.8	26.6	5.4	6.1	10.3	0	5	12	4.3
36	60	0.9	25.8	6.0	5.8	11.0	0	7	20	4.2

revised: 6.2.08

* measured with Uster Tensorapid

** measured with Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Schweiz

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhleryarn.com

internet: www.buhleryarn.com