



## 100 % gekämmte Extralangstapel-Baumwolle, Compact

### SwissCotton Compact - 100 % gekämmte Extralangstapel-Baumwolle - Compact: Garnrichtwerte für Konen

Garnnummer			Zugfestigkeit (5000mm/min.) *		Dehnung *	Egalität **	Imperfektionen **			Haarigkeit **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Dünn -50%	Dick +50%	Nissen +200%	H
30	50	1.2	26.9	7.1	6.1	10.8	0	4	8	3.9
40	68	1.3	26.9	7.8	5.8	12	0	10	17	3.3
50	85	1.3	25.9	8.7	5.7	12.3	1	15	30	2.9
60	100	1.4	25.4	8.9	5.4	12.8	4	25	45	2.8
70	120	1.4	24.9	9.2	5.2	13.5	8	45	65	2.7
80	135	1.5	24.5	10.6	4.9	14	20	50	75	2.7
100	170	1.7	23.4	12	4.8	15	50	70	110	2.4
118	220	1.8	21.5	14.7	4.7	16	120	110	150	2.2
132	224	2	20.4	16.6	4.5	17.3	260	210	210	2

aktualisiert: 10.5.10

\* gemessen mit Uster Tensorapid

\*\* gemessen mit Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Schweiz

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: [info@buhleryarn.com](mailto:info@buhleryarn.com)

internet: [www.buhleryarn.com](http://www.buhleryarn.com)