



Micro Modal, AirJet

SwissModal Micro - 100 % Micro Modal: yarn on cones

Ne	yarn count		strength (5000mm/min.) *		elongation *	mass variation **	imperfections **			hairiness **
	Nm	CV%	cN/tex	CV%	D%	CV%	thin -50%	thick +50%	neps +200%	H
30	50	0.8	21.2	7	8.4	10.9	0	2	8	3.6
40	68	0.8	19.4	8.5	8.4	12.1	1	4	9	3.9
50	85	0.8	18.5	10.5	7.2	13.6	15	12	15	3.6
60	100	0.8	17.2	11.7	6.7	14.6	40	30	35	3.4
70	120	0.8	17.4	12.6	7.1	16	110	60	100	2.7

revised: 08.05.2012

* measured with Uster Tensorapid

** measured with Uster Tester 4

Hermann Bühler AG

Spinning Mill

8482 Sennhof (Winterthur)

Switzerland

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhleryarn.com

internet: www.buhleryarn.com