

100 % extra long staple cotton yarn, royalspun

SwissCotton Royal - 100 % extra long staple cotton yarn: yarn on cones

Garnnummer			Zugfestigkeit (5000mm/min.) *		Dehnung *	Egalität **	Imperfektionen **			Haarigkeit **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Dünn -50%	Dick +50%	Nissen +200%	H
12	20	0.8	24.5	4.8	6.7	7.4	0	3	3	7.5
20	34	0.8	27.4	4.9	6.6	8.8	0	3	3	4.9
24	40	0.8	26.5	5.0	6.4	9.2	0	4	5	4.5
30	50	0.9	26.4	5.3	6.0	10.0	0	5	7	4.1
36	60	0.9	25.8	5.9	5.8	10.5	0	5	11	4.0

revised: 15.8.11

* measured with Uster Tensorapid

** measured with Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Schweiz

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhler yarn.com

internet: www.buhler yarn.com