



## Micro Modal, hilo de la continua de anillos, AirJet

### SwissModal Micro - 100 % Micro Modal: Información del hilo en los conos

Titulo del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **	Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H
30	50	0.8	21.2	7	8.4	10.9	0	2	8	3.6
40	68	0.8	19.4	8.5	8.4	12.1	1	4	9	3.9
50	85	0.8	18.5	10.5	7.2	13.6	15	12	15	3.6
60	100	0.8	17.2	11.7	6.7	14.6	40	30	35	3.4
70	120	0.8	17.4	12.6	7.1	16	110	60	100	2.7

revisado: 08.05.2012

\* medido con Uster Tensorapid

\*\* medido con Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Suiza

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhler yarn.com

internet: www.buhler yarn.com