

SwissCotton Ring - 100 % algodón extra larga: Información del hilo en los conos

Titulo del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **	Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H
30	50	1.2	25.9	6.8	5.7	10.8	0	6	10	4.7
40	68	1.3	24.7	7.5	5.3	11.8	1	10	25	4.4
50	85	1.4	24.1	8.4	5.2	12.4	1	15	32	4.2
60	100	1.5	23.2	8.7	5.0	13.0	4	25	55	3.9
70	120	1.5	22.4	9.8	4.8	14.0	12	50	80	3.7
80	135	1.6	22.0	10.0	4.7	15.0	35	80	135	3.4
90	150	1.7	21.3	11.2	4.7	15.6	65	110	180	3.3
100	170	1.8	20.9	12.2	4.6	16.3	100	140	190	3.1
105	180	1.8	20.1	12.5	4.3	16.9	160	180	240	3.2
110	186	1.9	20.4	13.6	4.2	17.2	220	220	160	2.9

revisado: 15.8.11

SwissCotton Organic - 100 % algodón extra larga, biológico: Información del hilo en los conos

Titulo del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **	Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H
30	50	1.2	23.5	6.9	5.6	10.8	0	6	14	5.1
36	60	1.2	22.5	7.1	5.8	11.5	0	10	22	5.1
40	68	1.2	22.0	7.7	5.6	11.8	1	10	25	4.5
50	85	1.3	21.8	8.5	5.5	12.7	2	20	50	4.2
60	100	1.4	21.5	8.8	5.4	13.0	3	30	60	3.9
70	120	1.6	20.2	10.0	4.9	15.0	23	70	140	3.7
80	135	1.7	19.6	11.8	4.8	15.9	60	90	160	3.7
90***	150	1.8	22.4	11.8	5.0	15.5	45	75	120	2.6
95***	160	1.8	24.0	11.8	4.6	1.4	30	60	120	2.5

revisado: 15.8.11

* medido con Uster Tensorapid

** medido con Uster Tester 4

*** Kompakt

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Suiza

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhler yarn.com

internet: www.buhler yarn.com