

**SwissCotton Royal - 100 % algodón extra larga: Información del hilo en los conos**

Titulo del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **	Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H
12	20	0.8	24.5	4.8	6.7	7.4	0	3	3	7.5
20	34	0.8	27.4	4.9	6.6	8.8	0	3	3	4.9
24	40	0.8	26.5	5.0	6.4	9.2	0	4	5	4.5
30	50	0.9	26.4	5.3	6.0	10.0	0	5	7	4.1
36	60	0.9	25.8	5.9	5.8	10.5	0	5	11	4.0

revisado: 15.8.11

\* medido con Uster Tensorapid

\*\* medido con Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Suiza

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: [info@buhleryarn.com](mailto:info@buhleryarn.com)

internet: [www.buhleryarn.com](http://www.buhleryarn.com)