

### SwissCotton Silver - 100 % algodón extra larga con X-Static®: Información del hilo en los conos

XA: 95% algodón extra larga / 5% X-Static

XB: 90% algodón extra larga / 10% X-Static

Título del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **		Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H	
16 XA	28	0.8	23.8	5.6	6.4	0.0	0	0	0	6.6	
16 XB	28	0.8	23.0	5.8	6.4	0.0	0	0	0	6.4	
20 XA	34	0.8	24.4	5.8	6.3	0.0	0	0	0	5.4	
20 XB	34	0.8	24.1	6.2	6.3	0.0	0	0	0	5.2	
30 XA	50	0.9	23.8	6.4	5.8	0.0	0	0	0	4.7	
30 XB	50	0.9	23.4	6.7	5.8	0.0	0	0	0	4.6	
40 XA	68	0.9	22.3	7.1	5.5	0.0	0	0	0	4.6	
40 XB	68	1.0	22.0	7.2	5.5	0.0	0	0	0	4.2	
50 XA	85	1.0	22.2	7.9	5.3	0.0	0	0	0	4.1	
60 XA	100	1.0	20.5	8.0	5.2	0.0	0	0	0	4.1	
60 XB	100	1.0	19.8	8.2	4.8	0.0	0	0	0	3.9	

revisado: 3.1.11

\* medido con Uster Tensorapid

\*\* medido con Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Schweiz

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: [info@buhleryarn.com](mailto:info@buhleryarn.com)

internet: [www.buhleryarn.com](http://www.buhleryarn.com)